

Fluoro Chemical

2-(Perfluorohexyl)ethyl methacrylate

1H,1H,2H,2H-Perfluorooctylmethacrylate 95%
 1,1,2,2-Tetrahydroperfluorooctyl methacrylate
 Temac-6
 2-Methylpropenoic acid 3,3,4,4,5,5,6,6,7,7,8,8,8-tridecafluorooctyl
 Methacrylic acid 2-(tridecafluorohexyl)ethyl ester
 2-(Perfluorohexyl)ethyl methacrylate, 3,3,4,4,5,5,6,6,7,7,8,8,8-Tric
 2-methylprop-2-enoate
 1H,1H,2H,2H-Tridecafluorooct-1-yl methacrylate 99%
 2-(Perfluorohex-1-yl)ethyl methacrylate, 3,3,4,4,5,5,6,6,7,7,8,8,8-1
 2-methylprop-2-enoate
 1H,1H,2H,2H-Tridecafluoro-n-octyl Methacrylate (stabilized with
 3,3,4,4,5,5,6,6,7,7,8,8,8-Tridecafluorooctyl methacrylate contains 1
 4-tert-butylcatechol as inhibitor, 97%
 1H,1H,2H,2H-Tridecafluoro-n-octyl Methacrylate (stabilized with
 2-propenoic acid, 2-methyl-, 3,3,4,4,5,5,6,6,7,7,8,8,8-tridecafluoroo
 2-(PERFLUOROHEXYL)ETHYL METHACRYLATE
 3,3,4,4,5,5,6,6,7,7,8,8,8-TRIDECAFLUOROCTYL METHACRYL
 1H,1H,2H,2H-PERFLUOROCTYL METHACRYLATE
 Perfluorooctylmethacrylate
 1H,1H,2H,2H-Perfluorooctyl methacrylate 95%

DESCRIPTION

TYPE



TYPICAL

PROPERTIES

Appearance	Colorless transparent liquid
Purity (%)	≥98
Density (g/cm³)	1.496 g/mL at 25 ° C(lit.)
Melting point (°C)	50.77°C
CAS No.	2144-53-8
Boiling point	92 ° C8 mm Hg(lit.)
MF	C12H9F13O2
Flash(ing) point	>230 ° F
Refractive index	n ₂₀ /D 1.346(lit.)
MW	432.18

APPLICATION ●

STORAGE

AND

HANDLING

- Available in 25kg/barrel
- Store products in tightly closed original containers at 5-35°C
- Non danger product