



Water-based acrylic emulsion

SA-110 Modified silicone acrylic emulsion for exterior wall paint

| DESCRIPTION | SA-110 is modified silicone acrylic emulsion specialized in the external wall coating. It has good properties of scrub resistance, water resistance, used for real stone paint and multicolour paint | |
|----------------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------------------------------------------|
| ТҮРЕ | Modified silicone acrylic copolymer emulsion | |
| KEY FEATURES | Low VOC, excluding APEO, green environmental protection Mixed with protective colloid have good intermiscibility Since using emulsion crosslinking technology and uv curing oligomers technology, thus can make both soft and pollution resistance of paint film Micelle outer adopts special anchor groups, can effectively improve the adhesion between the layers between elastic coatings with primer and early wet adhesion The preparation of multi-color excellent white water resistance, water resistance and weatherability | |
| TYPICAL PROPERTIES | Appearance | Milky white emulsion with light blue shade |
| | рН | 7-9 |
| | Solid content | 47±1% |
| | Ionicity | Anionic |
| | Viscosity(25°C) | 1000-4000 cPs |
| | MFFT | 22 ℃ |
| | Ionic diameter | 0.1-0.2µm |
| | TG | 36℃ |
| APPLICATION | High-grade water-based paint High weather resistance exterior wall coating Mainly used for load-bearing emulsion multi-color continuous phase | |
| STORAGE AND HANDLING | 200kg/Plastic Barrel Store products in tightly closed original containers at 5-35°C, avoid freezing and high temperature, Shelf life: 9 months from delivery date According to non-dangerous goods transport | |

Add.: Hefei city, Anhui province, China Mob: +86 15755193346