



Waterproof Coating

PU-110 One Component Hydrophilic Water-Soluble

Polyurethane Water-stop Foam Gel/Flex

DESCRIPTION

It is conventional one component water-soluble polyurethane hydrophobic foam, react with water rapidly to be solidified and expansion to sealing the crack. After reaction with water to form milk-white elastic gel, with advantage performances of fast speed, high strength, and little shrinkage, strong penetration-proof etc., widely used in waterproof works such as the tunnel, the subway, dam, underground garage, sewers, etc.

TYPE

One Component Water-Soluble Polyurethane

KEY FEATURES

- Low viscosity, water quick dispersion happening reaction, forming impervious elastic colloidal concretion body, has the good plugging stop-water performance.
- With water formed ivory elastic colloidal concretion body, has high compressive strength, low temperature resistance, good elasticity, penetration-proof quality is good wait for a characteristic.
- Can permeate into crack depth, reaction after forming institutional concretion body omni-directional fill plugging cracks.
- Good expansion, good performance of reaction with large volume water.

PU-110A Gel Type

	Appearance	Yellowish transparent liquid
	Density (g/cm ³)	1.0-1.2
	Viscosity (mpa.s)	200-300
	Gel time (s)	10-50
TYPICAL	Expansion Ratio (%)	20-30
	Water Embracing (s)	45-80 (5-15 times water)
PROPERTIES	PU-110B Flex Type	
	Appearance	Yellowish transparent liquid
	Density (g/cm ³)	1.0-1.2
	Viscosity (mpa.s)	200-300
	Gel time (s)	10-60

Anhui Sinograce Chemical Co., Ltd. Tel: +86-0551-63459511

Expansion Ratio (%)

Water Embracing (s)

Email: sales@sinogracechem.com

Add.: Hefei city, Anhui province, China

50-100 (5-15 times water)

50-200

Mob: +86 15855525589





- Pool, towers, basement, shelter building such as irrigation seam plugging and waterproof coating.
- Metal and concrete pipe shaft preservation and steel structure of the corrosion.
- Underground tunnel, buildings foundation reinforcement.

APPLICATION

- Architectural engineering distortion seam, construction seam, structural cracks plugging and reinforcement.
- Port and dock pier, DAMS, hydropower station with the curtain grouting reinforcement plugging.
- Geological drilling slurry-supported plugging, oil exploitation of water and mine where water gushing closed etc.

STORAGE

• Available in 25 kg/ barrel or 10 kg/ barrel

AND

• Store products in tightly closed original containers at 5-40°C

HANDLING

Shelf life: 9 months from delivery dateAccording to non-dangerous goods transport

Anhui Sinograce Chemical Co., Ltd. Tel: +86-0551-63459511

Email: sales@sinogracechem.com

Add.: Hefei city, Anhui province, China

Mob: +86 15855525589